

Technical Data Sheet



Eclectic Products, Inc.
Manufacturing Facility
101 Dixie Mae Drive
Pineville, Louisiana
eclecticproducts.com
800.349.4667

ISO 9001:2008
Compliant
Quality Management
Systems

Administration Office
Eugene, Oregon
eclecticproducts.com
800.693.4667



Net Wt 2.0 lb Kit
Net Wt 8.0 lb Kit

AMAZING GOOP® COAT-IT®

WATERPROOF EPOXY SEALER and PROTECTOR

PRODUCT DESCRIPTION

COAT-IT is a black epoxy sealer and coating that contains ceramic beads which provide extreme abrasion resistance. It also contains Kevlar® for toughness and graphite for lubricity. COAT-IT provides an armor type high-build coating that is sandable, paintable and waterproof! Coat-It also works well as a sealer that fills and seals hard-to-find leaks and cracks in aluminum, wood, fiberglass, steel and ferrocement.

WHERE TO USE / APPLICATIONS

Great for boat bottoms, decks/steps/ramps, RV roofs, hatches and hulls.

FEATURES AND BENEFITS

ABRASION RESISTANCE – Very High.

LUBRICITY – Exhibits high lubricity in marine application and will slide over rocky or abrasive surfaces.

EASE OF APPLICATION – Easy. Use throw-away applicators.

WATERPROOF – Yes. Unique epoxy sealer.

ADHESION – Excellent. Flake-resistant.

SUBSTRATES – Aluminum, Wood, Fiberglass, Steel, Ferrocement.

TECHNICAL INFORMATION

PHYSICAL PROPERTIES	
Heat deflection temperature:	116 °F (ASTM D648-264 psi)
Bond strength:	2,020 psi (mild steel to mild steel)
Flexural strength:	8,460 psi
Flexural modulus:	319,000 psi
Tensile strength:	6,180 psi
Tensile modulus:	457,000 psi
Elongation:	1.35%
Barcol hardness (GYZI-935):	79
WORKING PROPERTIES	
Color:	Black
Packaging:	2.0 lb or 8.0 lb units
Flash point:	200 °F (93 °C)
Mixing ratio:	7:1 by weight
Pot life:	35 minutes
Cure time:	10-12 hours @ 70 °F (21 °C)
Shelf life:	1 year
CHEMICAL RESISTANCE (after 30 days immersion in chemicals at 77 °F / 25 °C)	
	Weight Change, %
Sulfuric Acid, 3%:	<1.0%
Sodium Chloride, 10%:	<0.1%
Distilled Water:	<0.1%
Nitric Acid, 10%:	<0.1%
Hydrochloric Acid, 10%:	<0.1%
Acetic Acid, 5%:	<0.1%
Hydrogen Peroxide, 3%:	<0.1%

Technical Data Sheet



Net Wt 2.0 lb Kit
Net Wt 8.0 lb Kit

AMAZING GOOP® COAT-IT®

WATERPROOF EPOXY SEALER and PROTECTOR

DIRECTIONS and APPLICATION NOTES

Read Directions and always test a small area before full use.

SURFACE PREPARATION

- Step 1 Use protective gloves to avoid getting COAT-IT on skin. In case of contact with skin, use plenty of soap and water to remove epoxy.
- Step 2 For small quantities, mix 7 parts of Part A and 1 part of Part B - **by weight** (not by volume).
- Step 3 A clean, freshly sanded surface is essential to creating a good bond. Remove all contaminants such as oil, grease, dirt and old coatings. Sand until there is a clean surface. Steel and/or aluminum boats should be sanded or cleaned with steel wool and treated with a marine phosphoric acid wash, such as Naval Jelly or Aluminum Bright, to remove any rust oxidation. Tape off boat sides if necessary.
- Step 4 Gouges and deep holes should be filled with an epoxy or fairing compound before applying COAT-IT.
- Step 5 May be applied to dry or porous surfaces.

MIXING

- Step 1 Stir Part A container of COAT-IT until a uniform consistency occurs. Pour Part B into Part A container.
- Step 2 Sufficient stirring and mixing is the most important step for satisfactory results with COAT-IT. Mix with fold-into-center motion. Mix entire contents thoroughly for 6-7 minutes. Occasionally scrape bottom and sides of mixing container as well as mixing stick. Mixed material should be used within 30 minutes.
- Step 3 After mixing thoroughly, immediately pour material onto working surface. Do not leave mixed material in original container.

APPLICATION

- Step 1 Application can be readily completed with a toothed trowel, squeegee, short bristle throw-away brush or foam roller.
- Step 2 Working time is approximately 30 minutes.
- Step 3 Adequate cure time is approximately 10-12 hours @ 70 °F/21 °C. Minimum application temperature 65 °F/18 °C. Application **surface** temperature range is 50 to 90 °F/10 to 32 °C. Cure time decreases with higher temperatures. Thicker coats cure faster than thin coats. A second coat of COAT-IT may be applied after the initial 10-12 hour cure period.
- Step 4 Clean tools with acetone or lacquer thinner. For maximum ultraviolet protection, allow COAT-IT to cure thoroughly, sand lightly and apply a good grade of marine paint. For deep repairs: allow 1st layer to dry before applying subsequent layers.

COVERAGE

- 2.0 lb Kit Approximately 20 sq ft*
8.0 lb kit Approxlmately 80 sq ft*

*depending upon the porosity of the surface and thickness applied

COAT-IT **is not** recommended for repairing blister pox in fiberglass hulls.
For technical assistance, call 800.767.4667.

HEALTH and SAFETY

This product contains epoxy resin and amine hardener. Before working with this product, read and become familiar with information concerning hazards, proper use and handling.

Product MSDS is available on line at:

eclecticproducts.com/msds/coatit_english_hardener_resin.pdf; to request a hard copy of the MSDS, please send an e-mail to msds@eclecticproducts.com or call 800.333.9826.

AMAZING GOOP® COAT-IT®

WATERPROOF EPOXY SEALER and PROTECTOR

LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.