

Technical Data Sheet



Eclectic Products, Inc.
Manufacturing Facility
101 Dixie Mae Drive
Pineville, Louisiana
eclecticproducts.com
800.349.4667

ISO 9001:2008
Compliant
Quality Management
Systems

Administration Office
Eugene, Oregon
eclecticproducts.com
800.693.4667



E6100[®] Non-Sag Formula

INDUSTRIAL ADHESIVES

PRODUCT DESCRIPTION

E6100[®] is a unique NON-SAG, non-flammable industrial adhesive formulated to meet high-performance requirements. It permanently adheres to more surfaces than virtually any other adhesive, providing exceptional adhesion to wood, metal, glass, fiberglass, ceramics, masonry, concrete, asphalt, leather, rubber, PVC, neoprene, vinyl and many plastics. This NON-SAG formula will not drip or run and is highly recommended for use in applications requiring vertical hold. E6100 maintains its flexible bond in extreme cold temperatures, will not crack or become brittle and is excellent for bonding items subject to vibration. For applications exposed to direct sunlight, paint over E6100 after curing.

WHERE TO USE / APPLICATIONS

- counter top assembly
- cracks in vertical brick & mortar
- HVAC systems
- leaking containers/pipes
- locking down fasteners against vibration
- seams in trailers
- installing and securing building signs
- wall paneling
- roof flashing/shingles
- garage door assemblies
- auto upholstery/paneling/molding and much more!

FEATURES AND BENEFITS

EASY TO USE – 10.2 fl oz cartridge fits into standard cartridge gun

FLEXIBLE – does not become brittle in cold weather and bonds items subject to vibration

CHEMICAL RESISTANT – safe for applications exposed to dilute acids and dilute caustics

ABRASION RESISTANT – great for bonding objects subject to normal wear

WATERPROOF – can be submerged in fresh and salt water after complete cure

PAINTABLE – paint to match surrounding area or make UV resistant

TECHNICAL INFORMATION

PROPERTIES	
UNCURED MATERIAL	
Color:	Clear, White, Gray & Black
VOC:	2.0 grams/liter
Solvent:	Perchloroethylene
Non-flammable:	Yes
Density:	11.0 +/-0.1 lbs/gal
Solids:	30% by weight, 40% by volume
Viscosity:	Non-sag; 100,000 cps
Tack time:	~ 4 minutes
Set time:	20 minutes*
Full cure time:	Thin film: 24 hours / Thick film: 48-72 hours
Storage:	Store in dry area between 50 and 80 °F (10 and 27 °C)
Freeze/thaw stability:	Stable, allow product to warm to room temperature before using
Shelf life:	2 year (unopened)

*Depending on material, humidity and temperature.

Technical Data Sheet



E6100[®] Non-Sag Formula

INDUSTRIAL ADHESIVES

CURED MATERIAL	
Chemical resistance:	Excellent to water, dilute acids and dilute bases
Hardness:	80 Shore A
Dielectric strength:	400V/mil (ASTM D-149); this is the maximum voltage that can be applied to a given material without causing it to break down
Tensile strength:	3800 lb/in ² (ASTM D-412)
Elongation:	900% (ASTM D-412)
Temperature range:	-40 to 150 °F (-40 to 66 °C)
UV resistance:	Paint-over or use E6800
Paint-over time:	24 hours

ADHESION TEST – 180° Peel Strength Test - ASTM D 903				
Aluminum	Birch (wood)	Glass	PUC	Steel
35 pli	40 pli	34 pli	38 pli	45 pli

Avg. Max Load Measured in pli (pounds per linear inch)

CHEMICALS THAT HAVE LITTLE OR NO EFFECT ON E6000[®]

Acetic acid (5% and 10%)	E6000 [®] exhibits excellent resistance to water, dilute acids and dilute bases. Thin films of E6000 were immersed in various chemicals for two weeks and exhibited weight gains of less than 2% and tensile strength loss of less than 10%. These chemicals are listed on the left. All percentages are given by weight unless otherwise noted.
Ammonium hydroxide (3.4%)	
Ammonium nitrate (50%)	
Antifreeze	
Beer (3.2% alcohol by volume)	
Boric acid (3.1%)	
Distilled water	
Hydraulic oil	
Lactic acid (3.8%)	
Milk (fresh, tested at 40 °F)	
Motor oil (30w)	
Nitric acid (10% and 20%)	
Oxalic acid (3.1%)	
Phosphoric acid (30% and 60% as P ₂ O ₅)	
Potassium hydroxide (3.4%)	
Sodium carbonates (2.7%)	
Sodium chloride (10%)	
Sulfuric acid (3% and 10%)	
Wine (20% alcohol by volume)	

SOLVENTS THAT DISSOLVE E6000[®]

Chevron solvent 1100	These are common solvents that dissolve E6000 [®] when hardened samples were immersed. The dissolution with these solvents was not instantaneous and therefore does not preclude usage in all cases. Applications were an occasional splash or brief exposure is expected may be acceptable. Test a small area before full use.
Chlorothane NU	
Cyclohexane	
Gasoline	
Methylene chloride	
Perchloroethylene	
Propyl acetate	
Toluene	
1, 1, 1-Trichloroethane	

Technical Data Sheet



E6100[®] Non-Sag Formula

INDUSTRIAL ADHESIVES



DIRECTIONS and APPLICATION NOTES

- Step 1 Read directions and test small area before use.
- Step 2 Surface should be clean, dry and free of dirt.
- Step 3 For cartridges: Trim end of nozzle. Puncture inner seal.
- Step 4 Product can be used between 50 and 90 °F (10 and 32 °C).
- Step 5 For best results, roughen surface before use. For non-porous surfaces, apply a thin coat to each surface. Wait approximately 2 minutes before mating surfaces.
- Step 6 For maximum-strength bond, allow 24-72 hours for cure time.
- Step 7 Clean uncured adhesive with acetone or citrus-based solvents. Cured material may be removed by cutting or scraping. For prolonged storage after opening; for easy cap removal, apply a thin coat of petroleum jelly to the threads of the tube before replacing cap; for cartridge, cover or plug the opening of the nozzle.

For technical assistance, call 800.767.4667.

May damage finished surfaces. Avoid such contact until completely dry. Not recommended for use on polystyrene, polyethylene, polypropylene, Styrofoam™ or paper products, and any items that come into contact with food, drinking water or animals.

HEALTH and SAFETY

United States | Contains perchloroethylene and drometrizole. Harmful if inhaled. May cause dizziness, headache or nausea. May cause skin and respiratory tract irritation. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful. May produce allergic skin reaction. **WARNING:** This product contains a chemical known to the State of California to cause cancer. Avoid contact with eyes and skin. Use in a well-ventilated area. To avoid breathing vapors, open windows and doors or use other means to ensure fresh air entry during application and curing. Wash hands after use. If allergic reaction develops, discontinue use. **First Aid:** If you experience difficulty in breathing, move to fresh air. If symptoms persist, get medical attention. In case of eye contact, flush immediately with plenty of water; for skin, wash thoroughly with soap and water. If swallowed, do not induce vomiting. Keep out of reach of children.

Canada | FUMES MAY BE HARMFUL. MAY IRRITATE EYES. Do not breathe fumes. Do not get in eyes or on skin. Use only in a well-ventilated area. Keep out of reach of children.

FIRST AID TREATMENT : Contains perchloroethylene. If swallowed, call a Poison Control Centre or doctor immediately. Do not induce vomiting. If breathed in, move person into fresh air. If in eyes or on skin, rinse well with water for 15 minutes. May cause dizziness, headache or nausea. Intentional misuse by deliberately concentrating and inhaling the contents may be harmful. Open windows and doors during application and curing.

Before working with this product, read and become familiar with information concerning hazards, proper use and handling. MSDS is available on line at:

eclecticproducts.com/_msds/e6100_english_clear.pdf;

eclecticproducts.com/_msds/e6100_french_clear.pdf; to request a hard copy of the MSDS, please send an e-mail to msds@eclecticproducts.com or call 800.333.9826.

LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.