

Technical Data Sheet



Eclectic Products, Inc.
Manufacturing Facility
101 Dixie Mae Drive
Pineville, Louisiana
eclecticproducts.com
800.349.4667

ISO 9001:2008
Compliant
Quality Management
Systems

Administration Office
Eugene, Oregon
eclecticproducts.com
800.693.4667



US Packaging | Net Wt 4.0 oz Kit



CANADA Packaging | Net Wt 113.4 g Kit

AMAZING GOOP® MARINE



EPOXY PASTE

PRODUCT DESCRIPTION

MARINE EPOXY PASTE is a thick and creamy epoxy filler, formulated to easily fill holes, gouges, cracks, splits, fractures, rust-outs, dry rot, fiberglass gel coat blisters. It offers exceptional high impact resistance with no sag. **MARINE EPOXY PASTE** bonds permanently to fiberglass, all types of wood, plywood, steel, aluminum, copper, brass, cast iron, tile, ABS, PVC and most plastics. It forms a complete weatherproof bond, often stronger than the material being repaired. Once cured it can be sanded, ground, drilled, tapped, sawed, will accept self-tapping screws and can be painted with most paints.

WHERE TO USE / APPLICATIONS

Marine Epoxy Paste can be used for: keels and skegs, hulls and decks, pools and spas, boat blister pox repairs and seal leaks. Use on: fiberglass, wood, aluminum, metal and much more.

FEATURES AND BENEFITS

- FAST CURE TIME** – seals holes and leaks quickly; sets in 5 minutes; power sand in 20 minutes; cures in temperatures as low as 34 °F (1 °C)
- 100% SOLIDS** – will not shrink and maintains strength after full cure
- CHEMICAL RESISTANT** – can be used on or around objects exposed to gasoline, diesel fuel, motor oils, transmission and hydraulic fluids, antifreeze and most chemicals
- HEAT RESISTANT** – apply to objects reaching temperatures as high as 190 °F (88 °C) intermittently
- WATERPROOF** – remains waterproof after full cure

TECHNICAL INFORMATION

PHYSICAL PROPERTIES	
Non-volatile content:	100%
Compressive strength:	36,000 psi
Compressive ultimate strain:	20%
Shear strength:	2,700 psi
Tensile strength:	7,450 psi
Elongation:	3%
Modulus of elasticity:	2.0 x 10 ⁵ psi
WORKING PROPERTIES	
Color:	Light Beige
Packaging:	Net Wt 4.0 oz Kit
Mixing ratio:	1:1 by volume
Pot life (working time):	5 minutes @ 70 °F (21 °C)
Cure time:	20 minutes @ 70 °F (21 °C)
Shelf life:	3 years from manufacturing date (unopened)

Technical Data Sheet



AMAZING GOOP® MARINE

EPOXY PASTE



US Packaging | Net Wt 4.0 oz Kit



CANADA Packaging | Net Wt 113.4 g Kit

CHEMICAL RESISTANCE *after 30 days immersion in chemicals at 70 °F / 21 °C)			
Chemical	Weight Change, %	Flexural* Strength psi, (kg/cm)	Flexural* Strength retention
Sulfuric Acid, 3%:	+0.96	60,000 (4,219)	83%
Sodium Chloride, 10%:	+0.54	70,750 (4,975)	98%
Distilled Water:	+0.75	67,700 (4,761)	94%
Nitric Acid, 10%:	+1.11	53,350 (3,752)	74%
Hydrochloric Acid, 10%:	+0.81	49,450 (3,477)	68%
Acetic Acid, 5%:	+2.23	57,000 (4,008)	79%
Hydrogen Peroxide, 3%:	+0.90	66,400 (4,669)	92%
Petrohol 99 (MIL-F-05566):	0.00	74,900 (5,267)	100%
Hydrocarbon Test Fluid (MIL-H-3136):	+0.02	74,400 (5,232)	100%
Ethylene Glycol (MIL-E-5559)	0.00	73,700 (5,183)	100%

DIRECTIONS and APPLICATION NOTES

Read Directions and always test a small area before full use.

- Step 1 Clean area to be repaired. Remove all contaminants such as oil, grease, dirt, rust and paint.
- Step 2 For best results, roughen surface with coarse sandpaper or file.
- Step 3 Use a mixing stick (or similar object) to transfer equal portions of Resin (Side A) and Hardener (Side B) to a clean mixing container (preferably a new paper cup or bucket). If only a portion of the epoxy is necessary for a small application, reseal remaining epoxies in their individual containers for later use.
- Step 4 Stir and mix very thoroughly for 2 minutes. Always use a container for mixing, so both the Resin (Side A) and the Hardener (Side B) can be blended thoroughly.
- Step 5 Set/working time is: 5 minutes @ 70 °F/21 °C.
- Step 6 Epoxy can be sanded after fully cured. Wear dust mask when sanding.
- Step 7 Clean uncured epoxy from mixing tools with small amounts of acetone or lacquer thinner. Cured material may be removed by cutting or scraping

For technical assistance, call 800.767.4667.

NOTES: If contents on either side appear crystallized or solid, apply moderate heat (120 to 130 °F/49 to 54 °C) until contents return to soft putty state. Allow to cool before mixing Side A with Side B.

Do not apply fiberglass (polyester) resins over epoxy. Adhesion is poor and fiberglass resins may attack and soften epoxy resins or putties, such as AMAZING GOOP® Epoxy Paste. AMAZING GOOP® Epoxy Paste will withstand extreme heat.

AMAZING GOOP® MARINE Epoxy Paste may be tinted with powder colorants, most water-based colorants and food dye. It holds its bond even underwater. Cure epoxy above water 3 to 7 days before submerging. Stays put - no slump or sag.



AMAZING GOOP[®] MARINE

EPOXY PASTE

HEALTH and SAFETY

DANGER – CORROSIVE. SEVERE EYE AND SKIN IRRITANT. POTENTIAL SKIN SENSITIZER. Side A contains epichlorohydrin based epoxy resin. May irritate eyes and skin. May produce allergic skin reaction. Side B contains aliphatic amine resin. Harmful if inhaled. May cause severe irritation to eyes and skin. Use with adequate ventilation.

First Aid: In case of contact, flush eyes or skin with plenty of water. If breathed in, move person to fresh air. Get medical attention if symptoms persist. Keep out of reach of children.

Before working with this product, read and become familiar with information concerning hazards, proper use and handling.

Product MSDS is available on line at:

eclecticproducts.com/_msds/marine_english_hardener_resin.pdf; to request a hard copy of the MSDS, please send an e-mail to msds@eclecticproducts.com or call 800.333.9826.

LIMITED WARRANTY

The product is warranted against any defect in materials or workmanship under normal use for a period of 180 days after the date of purchase. The product is also warranted under any implied warranties provided under applicable state law, including, without limitation, the implied warranty of merchantability and the implied warranty of fitness for a particular purpose, for a period of 180 days after the date of purchase. This warranty covers only the original buyer of the product. For warranty service, the buyer should contact the store where the product was purchased, or write Eclectic Products, Inc., P.O. Box 4450, Pineville LA 71361 or call 800.767.4667. This warranty gives you specific legal rights, and you also have other rights, which vary from state to state.